

## PRODUCT DATA

## 2990 STAINBLOCKER

### DESCRIPTION

RUST-OLEUM® HARD HAT Aerosol 2990 Stainblocker is a matt white high-pigmented coating based on a plasticized acrylic resin for the permanent isolation of problem stains from nicotine, soot, tar and rust and the effects of moisture, graffiti and a numerous other colourings.

### RECOMMENDED USES

RUST-OLEUM® HARD HAT Aerosol 2990 Stainblocker is a renovation paint which can be applied directly on ceilings, plaster, cement, wood, concrete, wallpaper, isolation walls, old paints, etc.

RUST-OLEUM® HARD HAT Aerosol 2990 Stainblocker can be used as topcoat or can be recoated with standard wall paints.

### TECHNICAL DATA

Appearance:	Matt
Colour:	White
Propellant:	Propane/Butane
VOC-content:	532 g/l

<b>Drying times</b>	20°C/50% r.h.
Tack free:	5 minutes
To recoat:	Wet in wet / after ½ hour
Full hardness	24 hours

### COVERAGE

Theoretical: 2,1 m<sup>2</sup> per aerosol at 30 µm dry  
Practical coverage depends on many factors such as roughness of the substrate and material losses during application.

### SURFACE PREPARATION

Remove dirt, grease, oil, loose rust and all other surface contaminants by appropriate means. Sand intact coatings to roughen the surface slightly. The surface must be clean and dry during application.

### DIRECTION FOR USE

Remove cover cap. Shake vigorously for at least one minute after the rattle of mixing ball is heard. Shake frequently during use. Hold can approx. 25 cm from surface. Use back and forth motion keeping can parallel with surface. Ensure that can is in motion when spray button is pressed to avoid runs and sags. Apply several thin layers at a few minutes interval to achieve adequate coating thickness.

After use turn can upside down and press spray button for 2 - 3 seconds to clean valve.

### APPLICATION CONDITIONS

For optimum results the relative humidity should be below 85% and the temperature of the can above 0°C.

### SAFETY

Consult Safety Data Sheet and Safety Information printed on the can.

### SHELLIFE CONDITIONS

3 years from date of production, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35° C.

#### Rust-Oleum Netherlands B.V.

Braak 1, 4704 RJ  
P.O. Box 138, 4700 AC  
Roosendaal, The Netherlands  
T +31 (0)165 593 636  
F +31 (0)165 593 600  
[info.nl@ro-m.com](mailto:info.nl@ro-m.com)  
[www.ro-m.com](http://www.ro-m.com)

#### N.V. Martin Mathys S.A

Kolenbergstraat 23  
B - 3545 Zelem  
Halen, Belgium  
T +32 (0)13 460 200  
F +32 (0)13 460 201  
[info.be@ro-m.com](mailto:info.be@ro-m.com)  
[www.ro-m.com](http://www.ro-m.com)

#### Rust-Oleum France S.A

11, Rue Jules Verne, B.P. 39  
95322 St-Leu-la-Forêt Cedex  
France  
T +33 (0)130 400 044  
F +33 (0)130 409 980  
[info.fr@ro-m.com](mailto:info.fr@ro-m.com)  
[www.ro-m.com](http://www.ro-m.com)

#### Rust-Oleum UK Ltd.

Unit 5D, Alexandra Way  
Ashchurch B. Centre,  
Tewkesbury, Gloucestershire  
GL20 8NB, United Kingdom  
T +44 (0)1684 273 333  
F +44 (0)1684 273 331  
[info.uk@ro-m.com](mailto:info.uk@ro-m.com)  
[www.ro-m.com](http://www.ro-m.com)

#### Rust-Oleum Mathys Italia s.r.l.

Via Mazzetta 36, 13856  
Vigliano Biellese BI, Italia  
T +39 015 8122 160  
F +39 015 8122 161  
[info.it@ro-m.com](mailto:info.it@ro-m.com)  
[www.ro-m.com](http://www.ro-m.com)